CHEMI-CON SUPERCAPACITOR



- Suitable for electricity storage, battery assistance, short-term backups, etc.
- · Also suitable for kinetic energy recapturing, start/stop application for automobile.



SPECIFICATIONS

Items	Specifications					
Operating Temperature	$-40^{\circ}\text{C} \sim +70^{\circ}\text{C}$					
Capacitance Tolerance	±10% (K)					
Temperature Characteristics	Capacitance Change $\leq \pm 30\%$ of the measured value at 20°C					
	Internal Resistance Change	\leq 1200% of the internal resistance maximum value given in the ratings tables	(-40°C)			
Load Life Test	After the capacitors are subjected to the rated DC voltage at 70°C for 2000 hours, the following specifications shall be satisfied when they are restored to 20°C.					
	Capacitance Change	$\leq \pm 30\%$ of the initial measured value at 20°C				
	Internal Resistance Change	\leq 300% of the internal resistance maximum value given in the ratings tables				
Bias Humidity Test	After the capacitors are left at 60°C and 90 to 95%RH for 500 hours, without voltage applied, the following spe be satisfied when they are restored to 20°C.					
	Capacitance Change	\leq ±30% of the initial measured value at 20°C				
	Internal Resistance Change	\leq 300% of the internal resistance maximum value given in the ratings tables				

♦ STANDARD RATINGS

DXE series

Rated Voltage	Capacitance		Nominal Case Size		Internal Resistance		Weight*1	Energy Storage*2	Part No.
[V]	Typ. (rated) [F]	Min. [F]	φ D[mm]	L[mm]	Typ. [mΩ]	Max. [mΩ]	[g]	[Wh]	Fait NO.
	400	360	40	65	2.1	2.5	120	0.4	DDXE2R5LGN401KB65S
2.5	800	720		105	1.1	1.3	200	0.7	DDXE2R5LGN801KBA5S
2.5	1200	1080		150	0.8	1.0	280	1.1	DDXE2R5LGN122KBF0S
	1400	1260		150	1.1	1.3	280	1.3	DDXE2R5LGN142KBF0S

*1 Reference data

*2 The energy storage capacity (Wh) described in this product is calculated based on 「電気及び電子機器用電気二重層キャパシタの輸送 に関する手引書」(Japanese only) by JEITA.

PART NUMBERING SYSTEM

Image: Contract of the second seco
Category

DLCAP[™] DXE series

DIMENSIONS [mm]

